



## All-State Overlay 5659

General purpose hardfacing metal-cored gas shielded overlay with excellent abrasion and impact resistance. Best with Argon/CO2 mixtures, 100% CO2 okay. Deposit hardness 55-59 RC