

OK 67.70



Acid rutile MMA-electrode giving an over alloyed weld metal. Suitable for welding acid resistant stainless steels to mild and low alloyed steels. Also suitable for welding buffer layers when surfacing mild steel with acid resistant stainless steel weld metal.

Classifications	SFA/AWS A5.4 : E309LMo-17 EN ISO 3581-A : E 23 12 2 L R 3 2 CSA W48 : E309LMo-17 Werkstoffnummer : 1.4459
Approvals	ABS SS to C&C/Mn steels BV 309Mo CE EN 13479 CWB E309LMo-17 DB 30.039.05 DNV-GL VL 309 Mo LR SS/CMn NAKS/HAKC 3.2 mm RINA 309Mo Seproiz UNA 272580 VdTUV 02424

Approvals are based on factory location. Please contact ESAB for more information.

Welding Current	DC+, AC
Ferrite Content	FN 12-22
Alloy Type	Austenitic CrNi
Coating Type	Acid Rutile

Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
ISO			
As Welded	510 MPa (74 ksi)	610 MPa (88 ksi)	32 %

Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
ISO		
As Welded	20 °C (68 °F)	50 J (37 ft-lb)
As Welded	-20 °C (-4 °F)	35 J (26 ft-lb)

Typical Weld Metal Analysis %

C	Mn	Si	Ni	Cr	Mo	N	Ferrite FN
0.02	0.6	0.8	13.4	22.5	2.8	0.09	18

Deposition Data

Diameter	Current	Voltage	Number of electrodes/ kg weld metal	Burn-off Time/ Electrode	Deposition Efficiency %	Deposition Rate @ 90% I max
2.0 x 300.0 mm (5/64 x 11.8 in.)	40-60 A	26 V	147	48 sec	58 %	0.6 kg/h (1.3 lb/h)
2.5 x 300.0 mm (0.098 x 11.8 in.)	50-90 A	29 V	94	45 sec	57 %	0.9 kg/h (2.0 lb/h)
3.2 x 350.0 mm (1/8 x 13.8 in.)	60-120 A	27 V	47	61 sec	59 %	1.4 kg/h (3.1 lb/h)
4.0 x 350.0 mm (5/32 x 13.8 in.)	85-180 A	31 V	32	56 sec	61 %	2.0 kg/h (4.4 lb/h)
5.0 x 350.0 mm (0.197 x 13.8 in.)	110-250 A	30 V	20	64 sec	59 %	2.7 kg/h (6.0 lb/h)