

OK Flux 10.83

Agglomerated, aluminate-rutile, low basicity flux for Submerged Arc Welding. High welding speeds. Smooth weld beads and excellent slag detachability. For general construction, membrane wall panels, beam fabrications, automotive (wheels), etc. Primarily used with single- or twin-arc wire systems. For DC and AC. For single pass butt welds, overlap welds and fillet welds at high speeds.

Classifications	EN ISO 14174 : S A AR 1 85 AC
Approvals	CE EN 13479

Approvals are based on factory location. Please contact ESAB for more information.

Slag Type	Aluminate-rutile
Alloy Transfer	High Silicon, no Manganese alloying
Density	nom 1.2 kg/dm ³
Basicity Index	nom 0.3
Grain Size	0.2-1.6 mm (10x65 mesh)

Flux Consumption

Volts	kg Flux / kg Wire DC+	kg Flux / kg Wire AC
26 V	0.7 kg	0.6 kg
30 V	1.0 kg	0.9 kg
34 V	1.3 kg	1.2 kg
38 V	1.6 kg	1.4 kg

Dimensions	Amps	Travel Speed
Ø 4.0 mm	580 A	55 cm/min

Classifications

Wire	SFA/AWS - EN ISO	EN - As Welded	AWS - As Welded	AWS - PWHT
OK Autrod 12.10	A5.17:EL12/ 14171-A:S1	14171-A: S 38 Z AR S1	A5.17: F7AZ-EL12	A5.17: F6PZ-EL12
OK Autrod 12.22	A5.17:EM12K/ 14171-A:S2Si	14171-A: S 42 Z AR S2Si	A5.17: F7AZ-EM12K	A5.17: F7PZ-EM12K

Approvals

Combined with Wire	CE	VdTÜV
OK Autrod 12.22	•	•

Typical Mechanical Properties

Combined with Wire	Condition	Yield Strength	Tensile Strength	Elongation	Charpy V-Notch
OK Autrod 12.10	As Welded AWS DC+ hr	440 MPa	520 MPa	30 %	30 J @ 20°C
OK Autrod 12.10	As Welded EN AC hr	430 MPa	500 MPa	27 %	50 J @ 20°C
OK Autrod 12.22	As Welded AWS DC+	470 MPa	560 MPa	26 %	50 J @ 20°C 30 J @ 0°C
OK Autrod 12.22	As Welded EN AC	470 MPa	550 MPa	26 %	70 J @ 20°C 50 J @ 0°C
OK Autrod 12.22	As Welded EN AC hr	470 MPa	550 MPa	26 %	70 J @ 20°C 50 J @ 0°C

Typical Weld Metal Analysis %

C	Mn	Si
OK Autrod 12.10 AC, 580A, 29V		
0.05	0.6	0.7
OK Autrod 12.10 DC+, 580A, 29V		
0.05	0.5	0.7
OK Autrod 12.22 AC, 580A, 29V		
0.06	1.0	0.8
OK Autrod 12.22 DC+, 580A, 29V		
0.05	0.9	0.8