

## OK Autrod 308H

A continuous solid corrosion resisting chromium-nickel wire for welding of austenitic chromium nickel alloys of 18% Cr - 8% Ni-type.

OK Autrod 308H has a good general corrosion resistance. The alloy has a high carbon content which makes this alloy suitable for applications used at higher temperatures. The alloy is used in chemical and petrochemical plants for welding of pipes, cyclones and boilers.

<b>Classifications Wire Electrode</b>	SFA/AWS A5.9 : ER308H EN ISO 14343-A : G 19 9 H
<b>Approvals</b>	NAKS/HAKC 1.2MM

Approvals are based on factory location. Please contact ESAB for more information.

<b>Alloy Type</b>	Austenitic 19% Cr - 9% Ni - High C
<b>Shielding Gas</b>	M12, M13 (EN ISO 14175)

### Typical Wire Composition %

C	Mn	Si	Ni	Cr	N	Nb	FN WRC-92
0.05	1.9	0.5	9.2	19.8	0.06	0.01	9

### Deposition Data

Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate
0.8 mm (0.030 in.)	50-140 A	16-22 V	3.4-11.0 m/min (134-433 in./min)	0.8-2.7 kg/h (1.8-6.0 lb/h)
1.0 mm (0.040 in.)	80-190 A	16-24 V	2.9-8.4 m/min (114-331 in./min)	1.1-3.1 kg/h (2.4-6.8 lb/h)
1.2 mm (0.047 in.)	180-280 A	20-28 V	4.9-8.5 m/min (193-335 in./min)	2.6-4.5 kg/h (5.7-9.9 lb/h)