

ESAB 7018-1 Prime



ESAB 7018-1 Prime is a reliable, high-quality electrode, providing high deposition rate and extra low moisture absorption. It provides excellent welding pool control, minimal spatter level, good arc strike and easy slag removal making it easy to weld with, including in out-of-position welding. Particularly suitable for welding high strength low-alloy steels. The low-temperature impact strength of the weld metal should be noted.

Classifications	SFA/AWS A5.1 : E7018H4 R SFA/AWS A5.1 : E7018-1H4 R CSA W48 : E4918-1-H4 EN ISO 2560-A : E 46 5 B 32 H5
Approvals	ABS 3Y H5 BV 3Y H5 CWB E4918-1-H4 DNV-GL 3Y H5

Approvals are based on factory location. Please contact ESAB for more information.

Welding Current	AC, DC+
Diffusible Hydrogen	< 4.0 ml/100g
Alloy Type	Carbon Manganese
Coating Type	Basic covering

Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
AWS			
As Welded	500 MPa (73 ksi)	590 MPa (86 ksi)	28 %

Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
AWS		
As Welded	-45 °C (-49 °F)	105 J (78 ft-lb)
As Welded	-50 °C (-58 °F)	100 J (74 ft-lb)

Deposition Data

Diameter	Current	Voltage	Number of electrodes/ kg weld metal	Burn-off Time/ Electrode	Deposition Efficiency %	Deposition Rate @ 90% I max
2.4 x 350.0 mm (3/32 x 13.8 in.)	80-110 A	22.6 V	65.8	63.5 sec	64 %	0.86 kg/h (1.9 lb/h)
3.2 x 350.0 mm (1/8 x 13.8 in.)	110-140 A	22.6 V	41.1	72 sec	62 %	1.22 kg/h (2.7 lb/h)
4.0 x 350.0 mm (5/32 x 13.8 in.)	140-200 A	23.2 V	28	72.5 sec	62 %	1.77 kg/h (3.9 lb/h)