

## Dual Shield 7100 LC

Dual Shield 7100 LC provides outstanding operator appeal with its easily controlled arc, improved operation at lower current levels, minimal spatter and easily removed slag. Dual Shield 7100 LC can be used with CO<sub>2</sub> or 75% Ar/25% CO<sub>2</sub> shielding, however pure CO<sub>2</sub> is recommended in applications where restraint is high.

<b>Classifications</b>	AWS A5.20 : E71T-1C-DH8/T-1MH8/T-9C-DH8/T-9MH8 AWS A5.36 : E71T1-C1A4-CS1-DH8 AWS A5.36 : E71T1-M21A2-CS1-H8 ASME SFA 5.36 ASME SFA 5.20
<b>Approvals</b>	ABS CWB CSA W48 E491T-9-H8 E491T-9M-H8 DNV-GL LR Seismic Certified "D"
<b>Industry</b>	Bridge Construction Civil Construction Industrial and General Fabrication Mobile Equipment Process Railcars Ship/Barge Building

Approvals are based on factory location. Please contact ESAB for more information.

### Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Reduction in Area	Elongation
<b>75% Ar - 25% CO<sub>2</sub></b>				
As Welded	572 MPa (83 ksi)	621 MPa (90 ksi)	64 %	26 %
<b>100% CO<sub>2</sub></b>				
As Welded	565 MPa (73 ksi)	560 MPa (81 ksi)	52 %	23 %

### Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
<b>75% Ar - 25% CO<sub>2</sub></b>		
As Welded	-18 °C (0 °F)	61 J (50 ft-lb)
As Welded	-29 °C (-20 °F)	42 J (31 ft-lb)
<b>100% CO<sub>2</sub></b>		
As Welded	-18 °C (0 °F)	92 J (68 ft-lb)
As Welded	-29 °C (-20 °F)	56 J (41 ft-lb)

### Typical Weld Metal Analysis %

C	Mn	Si	S	P
0.03	1.4	0.6	0.010	0.010

### Deposition Data

Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate	Deposition Efficiency %
<b>100% CO<sub>2</sub></b>					
1.2 mm (.045 in.)	145 A	24.5 V	508 cm/min (200 in./min)	1.6 kg/h (3.6 lb/h)	81.2 %
1.2 mm (.045 in.)	190 A	26 V	762 cm/min (300 in./min)	2.5 kg/h (5.4 lb/h)	81.4 %
1.2 mm (.045 in.)	235 A	27.5 V	1016 cm/min (400 in./min)	3.3 kg/h (7.3 lb/h)	82.5 %
1.2 mm (.045 in.)	265 A	29 V	1270 cm/min (500 in./min)	4.2 kg/h (9.3 lb/h)	82.8 %
1.4 mm (.052 in.)	145 A	25 V	381 cm/min (150 in./min)	1.5 kg/h (3.4 lb/h)	74.3 %
1.4 mm (.052 in.)	180 A	25.5 V	508 cm/min (200 in./min)	2.0 kg/h (4.5 lb/h)	74.6 %
1.4 mm (.052 in.)	230 A	29.5 V	1270 cm/min (500 in./min)	5.5 kg/h (12.2 lb/h)	82.3 %
1.4 mm (.052 in.)	235 A	27.5 V	762 cm/min (300 in./min)	3.2 kg/h (7.0 lb/h)	78.2 %

## Dual Shield 7100 LC

Deposition Data					
Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate	Deposition Efficiency %
1.4 mm (.052 in.)	285 A	28.5 V	1016 cm/min (400 in./min)	4.4 kg/h (9.8 lb/h)	81.3 %
1.4 mm (.052 in.)	370 A	30.2 V	1524 cm/min (600 in./min)	6.7 kg/h (14.7 lb/h)	82.7 %
1.6 mm (1/16 in.)	195 A	24.5 V	381 cm/min (150 in./min)	2.0 kg/h (4.5 lb/h)	73.7 %
1.6 mm (1/16 in.)	285 A	26 V	635 cm/min (250 in./min)	3.7 kg/h (8.1 lb/h)	79.4 %
1.6 mm (1/16 in.)	320 A	28 V	762 cm/min (300 in./min)	4.4 kg/h (9.7 lb/h)	79.9 %
1.6 mm (1/16 in.)	345 A	30 V	889 cm/min (350 in./min)	5.2 kg/h (11.5 lb/h)	80.7 %
1.6 mm (1/16 in.)	385 A	32 V	1016 cm/min (400 in./min)	6.1 kg/h (13.4 lb/h)	82.6 %
1.6 mm (1/16 in.)	445 A	32.5 V	1270 cm/min (500 in./min)	7.6 kg/h (16.7 lb/h)	82.8 %

Recommended Welding Parameters				
Wire Diameter	Current	Voltage	TTW Dist.	Wire Feed Speed
<b>100% CO<sub>2</sub></b>				
1.2 mm (.045 in.)	135-205 A	23-26 V	9.5-12.7 mm (3/8-1/2 in.)	432-737 cm/min (170-290 in./min)
1.2 mm (.045 in.)	175-230 A	25-27 V	12.7-19 mm (1/2-3/4 in.)	737-889 cm/min (290-350 in./min)
1.2 mm (.045 in.)	180-265 A	26-30 V	19-25.4 mm (3/4-1 in.)	889-1397 cm/min (350-550 in./min)
1.4 mm (.052 in.)	125-235 A	23-26 V	12.7-16 mm (1/2-5/8 in.)	330-711 cm/min (130-280 in./min)
1.4 mm (.052 in.)	215-290 A	25-29 V	16-19 mm (5/8-3/4 in.)	711-1016 cm/min (280-400 in./min)
1.4 mm (.052 in.)	250-350 A	29-31 V	19-25.4 mm (3/4-1 in.)	1016-1524 cm/min (400-600 in./min)
1.6 mm (1/16 in.)	165-270 A	25-28 V	16-19 mm (5/8-3/4 in.)	343-673 cm/min (135-265 in./min)
1.6 mm (1/16 in.)	245-345 A	27-30 V	19-25.4 mm (3/4-1 in.)	673-1016 cm/min (265-400 in./min)
1.6 mm (1/16 in.)	290-415 A	28-32 V	25.4-31.75 mm (1-1.25 in.)	1016-1270 cm/min (400-500 in./min)
<b>75% Ar - 25% CO<sub>2</sub></b>				
1.6 mm (1/16 in.)	285-400 A	28-32 V	25.4-31.75 mm (1-1.25 in.)	813-1168 cm/min (320-460 in./min)
1.6 mm (1/16 in.)	250-340 A	27-30 V	19-25.4 mm (3/4-1 in.)	610-813 cm/min (240-320 in./min)
1.6 mm (1/16 in.)	185-285 A	24-28 V	16-19 mm (5/8-3/4 in.)	356-610 cm/min (140-240 in./min)
1.4 mm (.052 in.)	245-355 A	28-32 V	19-25.4 mm (3/4-1 in.)	940-1372 cm/min (370-540 in./min)
1.4 mm (.052 in.)	225-295 A	27-30 V	16-19 mm (5/8-3/4 in.)	686-940 cm/min (270-370 in./min)
1.4 mm (.052 in.)	135-250 A	24-28 V	12.7-16 mm (1/2-5/8 in.)	317.5-686 cm/min (125-270 in./min)
1.2 mm (.045 in.)	185-265 A	27-29 V	19-25.4 mm (3/4-1 in.)	775-1194 cm/min (305-470 in./min)
1.2 mm (.045 in.)	165-225 A	24-27 V	12.7-19 mm (1/2-3/4 in.)	610-775 cm/min (240-305 in./min)
1.2 mm (.045 in.)	130-200 A	22-26 V	9.5-12.7 mm (3/8-1/2 in.)	356-610 cm/min (140-240 in./min)