



## All-State BRAZALOY 31

Light blue powder flux for sheet and extruded aluminum. Removes oxides at just below the melting point of aluminum. Performs to AWS A5.31, Type FB1-A and AMS 3412D Active from 1050°F to 1250°F.

### Typical Tensile Properties

Condition
Condition